



TruVis P4232

Product Data Sheet

PRODUCT/CLASS	Neopentyl glycol ester/Pentaerythritol ester; NPG/PE Polyol Ester	
MANUFACTURING LOCATION	Brownsville, Tennessee	
AVAILABILITY	US. Additional Country Availability information on request.	
MARKET	Industrial, Transportation	
USES/CLAIMS	Base Oil; Lubricant	
APPLICATIONS	Hydraulic, Refrigeration Compressor, Turbine, 4-Stroke	
PROPERTY	TYPICAL VALUE	TEST METHOD
VISCOSITY @ 40°C	32 cSt	ASTM D445-09
VISCOSITY @ 100°C	5.0 cSt	ASTM D445-09
VISCOSITY INDEX	80	
POUR POINT	- 8 °C	ASTM D5950-02
FLASH POINT, COC	200 °C	ASTM D92-05A
NOACK VOLATILITY, % LOSS	13.22	ASTM D5800A
SPECIFIC GRAVITY @ 20°C	0.956	ASTM D4052-09
COLOR	1.0	ASTM D1500
PURITY, ESTER CONTENT	99.0	ASTM D3465
ACID VALUE	0.05 mgKOH/g	ASTM D974-08
HYDROLYTIC STABILITY	+ 0.04 mgKOH/g Δ	ASTM D2619
MOISTURE CONTENT	50 ppm	ASTM E1064-08
SEDIMENT, INSOLUBLE CONTAMINATION	3.5 mg/L	

Customer Service:
1-800-554-9887
Fax: 401-724-6250