



TruVis P60175

Product Data Sheet

PRODUCT/CLASS	Dipentaerythritol ester; DiPE Polyol Ester	
MANUFACTURING LOCATION	Brownsville, Tennessee	
AVAILABILITY	US. Additional Country Availability information on request.	
MARKET	Industrial	
USES/CLAIMS	Base Oil; Lubricant	
APPLICATIONS	Oven Chain	
PROPERTY	TYPICAL VALUE	TEST METHOD
VISCOSITY @ 40°C	171 cSt	ASTM D445-09
VISCOSITY @ 100°C	17.1 cSt	ASTM D445-09
VISCOSITY INDEX	107	
POUR POINT	- 35 °C	ASTM D5950-02
FLASH POINT, COC	301 °C	ASTM D92-05A
NOACK VOLATILITY, % LOSS		ASTM D5800A
SPECIFIC GRAVITY @ 20°C	0.970	ASTM D4052-09
COLOR	1.0	ASTM D1500
PURITY, ESTER CONTENT	99.0	ASTM D3465
ACID VALUE	0.01 mgKOH/g	ASTM D974-08
HYDROLYTIC STABILITY		ASTM D2619
MOISTURE CONTENT	250 ppm	ASTM E1064-08
SEDIMENT, INSOLUBLE CONTAMINATION	3.5 mg/L	

Customer Service:
1-800-554-9887
Fax: 401-724-6250



Teknor Apex Company
505 Central Avenue
Pawtucket, Rhode Island 02861
www.teknorapex.com/truvis

The information contained herein was obtained on representative samples of the materials and is believed to be reliable. Teknor Apex welcomes an opportunity to discuss your specific requirements regarding sales specifications.