



TruVis TM3200

Product Data Sheet

PRODUCT/CLASS	Tritridecyl trimellitate (TTDTM); Diester	
MANUFACTURING LOCATION	Brownsville, Tennessee	
AVAILABILITY	US. Additional Country Availability information on request.	
MARKET	Industrial, Transportation	
USES/CLAIMS	Base Oil; Water Miscible Lubricant	
APPLICATIONS	Gear, Compressor, Chain (300°C), High Temp. Grease	
PROPERTY	TYPICAL VALUE	TEST METHOD
VISCOSITY @ 40°C	320 cSt	ASTM D445-09
VISCOSITY @ 100°C	20.0 cSt	ASTM D445-09
VISCOSITY INDEX	70	
POUR POINT	- 29 °C	ASTM D5950-02
FLASH POINT, COC	280 °C	ASTM D92-05A
NOACK VOLATILITY, % LOSS	1.75	ASTM D5800A
SPECIFIC GRAVITY @ 20°C	0.957	ASTM D4052-09
COLOR, PT CO	100	ASTM D1209-05
PURITY, ESTER CONTENT	99.0	ASTM D3465
ACID VALUE	0.10 mgKOH/g	ASTM D974-08
HYDROLYTIC STABILITY	+ 0.03 mgKOH/g Δ	ASTM D2619
MOISTURE CONTENT	500 ppm	ASTM E1064-08
SEDIMENT, INSOLUBLE CONTAMINATION	3.5 mg/L	

Customer Service:
1-800-554-9887
Fax: 401-724-6250



Teknor Apex Company
505 Central Avenue
Pawtucket, Rhode Island 02861
www.teknorapex.com/truvis-esters

The information contained herein was obtained on representative samples of the materials and is believed to be reliable. Teknor Apex welcomes an opportunity to discuss your specific requirements regarding sales specifications.